AMENDMENTS TO THE CLAIMS

Claim 1: (Currently Amended) A process for preparing trichlorosilan (HSiCl₃) by catalytic hydrodehalogenation of silicon tetrachloride (SiCl₄) in the presence of hydrogen and a supported catalyst, in which at least one metal or metal salt selected from among the elements of main group 2 of the Periodic Table of the Elements is used as catalyst at a temperature in the range from 300 to 1000°C₃.

wherein said supported catalyst comprises at least one metal or metal salt selected from the group consisting of calcium, strontium, barium, calcium chloride, strontium chloride, and barium chloride, and

wherein said at least one metal or metal salt has been applied to a support selected from the group consisting of leached glass, fused silica, a porous siliceous support and a SiO₂ support.

Claims 2 - 4: (Canceled)

Claim 5: (Previously Presented) The process as claimed in claim 1,

wherein

the supported catalyst used has a catalyst content, calculated as element, of from 0.1 to 10% by weight.

Claim 6: (Previously Presented) The process as claimed in claim 1,

wherein

an $SiCl_4/H_2$ mixture having a molar ratio of from 1:0.9 to 1:20 is brought into contact with the catalyst.

Application Serial No. 10/584,466 Response to Office Action mailed September 21, 2009

Claim 7: (Previously Presented) The process as claimed in claim 1,

wherein

the reaction is carried out in a fixed-bed reactor, in a fluidized-bed reactor or in a moving-bed reactor.

Claim 8: (Previously Presented) The process as claimed in claim 1,

wherein

the catalytic reaction is carried out at a temperature in the range from 600 to 950°C and a pressure of from 0.1 to 100 bar abs.

Claim 9: (Previously Presented) The process as claimed in claim 1,

wherein

the reaction is carried out at a space velocity of from 2000 to 30000 h⁻¹ and the gas stream has a linear velocity of from 0.01 to 10 m/s in the reactor.

Claim 10: (Previously Presented) The process as claimed in claim 1,

wherein

HSiCl₃ is isolated from the product mixture or the product mixture is used further directly.